

“Superpig”


Pig Grain



Glazed / Resined Pigsplits



Suede Pigsplits



Leathers tanned with Wet White technology.

They can be used as “chromium free” leathers for shoe lining, since they respect the limits.

Chemical tests performed proving the above are the following:

Tests Performed :

Total Chromium	UNI EN ISO 17072-2	≤ 200 mg/kg
Chromium VI	UNI EN ISO 17075	NOT DETECTED
Azo dyes	UNI EN ISO 17234-1	≤ 30 mg/kg
Pentachlorophenol	UNI EN ISO 17070	≤ 5 mg/kg
Tetrachlorophenol	UNI EN ISO 17070	≤ 0,5 mg/kg
Formaldehyde	UNI EN ISO 17226 1/2	≤ 50/150 mg/kg
Soluble Cadmium	UNI EN ISO 17072-1	≤ 0,1 mg/kg
Lead	UNI EN ISO 17072-1	≤ 3,0 mg/kg

RESISTENCE TO TEMPERATURE NOT OVER 80°/85°C - 175°/185°F